



## Technical data sheet

# MINPUR<sup>®</sup> SSP

## SBK-08 Structure putty powder

### SBK-08 Structure putty powder

#### Specifications

##### Product properties:

- ❶ For use as a structure putty on hard concrete floors, stairs etc. or as shotcrete powder for repair works on exposed concrete surfaces (sintered layer).
- ❷ Can be mixed with shotcrete powder Be-dunkel and SBK-08 colour pigments and is suitable for use as structure putty for formwork structures and gaps between formwork elements.
- ❸ Use only together with SBK-08 Rep-hell and Be-dunkel and only with the tested permanent impregnation Neutec LT 425, Synfola P-IP 20, Synfola P-IP Perl.

##### Storage:

Store in a dry place. Always keep the container tightly closed.

##### Storage life:

12 months from delivery date until use.

##### Disposal:

The product must not enter effluent or sewerage. Please comply with the applicable regulations for the proper disposal of waste at federal, cantonal and communal levels.

#### Instructions / use

##### Primer (adhesive surface):

The substrate must be clean and free from dust, fat and oil. SSP establishes a firm bond between upper and base material. Prime the base twice with pure M-10 (mixed water) for highly absorbent substrates (priming). The structure putty must always be applied on the same day as the primer.

##### SSP Structure putty:

Mix 1 part SSP with 0.3 to 0.6 parts **M-10** (mixing water) depending on the structure thickness.

##### SSP spray application: (no priming)

For use with low-pressure sprayers, 1 part SSP has to be mixed well with 1 part **M-10** (mixed water).

##### Working temperature:

8° – 30°C.

##### Cleaning of tools:

Use tap water to clean the tools.

## Technical data

<b>Form:</b>	Powder "Contains Portland cement / white cement"
<b>Use:</b>	Mix 1 part SSP with 0.3 to 0.6 parts M-10 (mixing water) depending on the structure thickness.
<b>Colour:</b>	whitish
<b>Packaging / delivery form:</b>	15 kg oval bucket
<b>Storage suitability:</b>	Always keep the container tightly closed and dry.
<b>Transportation regulations:</b>	Non-dangerous goods in terms of transportation.

## Hazard warnings

"Contains Portland cement / white cement"

H315 Causes skin irritation.  
 H318 Causes severe eye damage.  
 H335 May cause respiratory irritation.  
 P261 Avoid inhalation of dust..  
 P280 Wear protective gloves / eye protection.  
 P305+P351+P338 IN CASE OF CONTACT WITH EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.  
 P310 Immediately make a call to the POISON CONTROL CENTRE or medical doctor.  
 P304+P340 IF INHALED: Move the affected person so he/she can access fresh air and ensure unhindered breathing.  
 P403+P233 Store in a well-ventilated place. Always keep the container tightly closed.  
 P501 Dispose of contents/container in accordance with local/regional/national/international regulations.



The information provided here represents our best knowledge and experience to date. However, it implies no liability. Subject to amendments within the scope of technological progress and/or operational development. All information simply defines the specification of our products and services and implies no guarantee. It does not release the customer from his/her duty to carefully check the functions and possible applications of the products. The testing of product suitability is in the clear responsibility of the customer and has to be conducted by authorised personnel. The same applies to the protection of third-party property rights.

Version: January 2018

This document is superseded when a new edition is published.