

1



**Technical
data sheet**

M[®]INPUR[®] M-10 Mixed water

Primer and mixing liquid

for SBK-08 Concrete cosmetic products,

DP1 / IBB Boden and DP1 / IBB Wand coatings

Specifications

- ❶ For use as an adhesive surface (primer) and mixing liquid of SBK-08 Rep-hell (exposed concrete repair mortar), SSP (structure putty), and Be-dunkel (shotcrete powder).
- ❷ For use as an adhesive surface (primer) and mixing liquid for DP1 / IBB Boden and DP1 IBB Wand coatings.
- ❸ In connection with Be-dunkel, SSP and Rep-hell DP1 / IBB Boden and DP1 / IBB Wand coatings, only the tested impregnation and sealing products Neutec LT 425, Synfola P-IP 20, Synfola P-IP Perl, EP-W-15 Top shall be used.

Storage: Do not store below 8°C or above 25°C. Always keep the container tightly closed.

Storage life: 12 months from delivery date until use.

Disposal: The product must not enter effluent or sewerage. Please comply with the applicable regulations for the proper disposal of waste at federal, cantonal and communal levels.

Instructions / use

Primer (adhesive surface) / mortar mixtures:

The substrate must be clean and free from dust, fat and oil. **M-10** establishes a firm bond between upper and base material.

Apply pure **M-10** mixed water once or, in case of extremely absorbent substrate, twice. **Please note:** Always prime on the same day as the subsequent treatment.

Mortar mixtures: Mix 1 part **Rep-hell** and 0.2 - 0.3 parts **M-10** depending on coat thickness.

Structure putty: Mix 1 part **SSP** and 0.3 - 0.6 parts **M-10** depending on coat thickness.

Mix 1 part **Be-dunkel** with 1 part **M-10** for SBK-08 spraying use.

Working temperature: 8° – 30°C, protect unprocessed material from frost and heat.

Cleaning of tools: Use tap water to clean the tools.

Technical data

Form:	liquid
Density:	(20°C): approx. 1.03 g/cm ³
pH-value (20°C), 2% solution:	7.5 – 8.5
Colour:	white

Extended technical data

Packaging / delivery form:	10l canister
Storage:	Original container. Protect from strong heat. !! Store protected from frost!! Do not store below + 8 C° or above 25 C°.
Storage suitability:	Do not stack pallets , so as to avoid potential damage caused by pressure and shear stress.
Transportation regulations:	Non-dangerous goods in terms of transportation.

The information provided here represents our best knowledge and experience to date. However, it implies no liability. Subject to amendments within the scope of technological progress and/or operational development. All information simply defines the specification of our products and services and implies no guarantee. It does not release the customer from his/her duty to carefully check the functions and possible applications of the products. The testing of product suitability is in the clear responsibility of the customer and has to be conducted by authorised personnel. The same applies to the protection of third-party property rights.